WEICONLOCK®
Pipe and thread sealant

WEICONLOCK® AN 305-11 Pipe and thread sealing



Pipe and thread sealing | DVGW and drinking water approval

· higher viscosity

· medium strength

· disassembly with normal tools

Technical Data

Colour		white
Fluorescent		no
For thread connections up to		M 80 R 3"
Viscosity		17.000 - 50.000 ht mPa·s
Gap bridging up to max.		0,4 mm
Breakaway torque		7 - 10 Nm
Prevail torque		2 - 4 Nm
Shear strength Nmm² (DIN 54452)		4 - 6 N/mm²
Handling strength		20 - 40 min.
Final strength	(100 % strength)	5-10 h
Temperature resistance		-60°C to +150°C
Minimum shelf life	at room temperature	24 mon.
Compressive strength (free cutting steel / grub screw = 8.8)		
M 3x6	max.	1500 bar
M 4x6	max.	1500 bar
M 5x8	max.	1500 bar
M 6x10	max.	1500 bar
M 8x12	max.	600 bar
M 10x16	max.	200 bar

Approvals / Guidelines

Hygiene Institute	UBA KTW-BWGL

Surface Pre-Treatment

To achieve optimum results, the mounting parts should be degreased and cleaned, e.g. with WEICON Surface (roughen the surfaces, if required). WEICONLOCK can also be used on uncleaned surfaces, e.g. screws as delivered. However, the cleaner the surface, the better the results achieved.

Application

WEICONLOCK is applied evenly straight from the Pen with the help of the dosing tip; avoid direct contact between dosing tip/metal. Apply WEICONLOCK to the thread in circles. Screw the pipe thread together and tighten it to the desired alignment. When used as flange sealing, apply a continuous bead to one flange side, then assemble parts quickly and screw tight. Do not pour any WEICONLOCK back into the bottle that has already come into contact with metal. Even extremely small metal particles cause the adhesive to cure inside the bottle. Therefore, in serial production, the use of dosing devices is recommended.

Storage

Store WEICONLOCK in the unopened original container at room temperature. Avoid sources of heat and direct sunlight. The air inside the packaging helps maintain storage stability.

Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Accessories

10021433	Activator F, 200 ml, green
10001256	Dosing Tip L Size 1, 1 PCE

Available sizes

10019997	WEICONLOCK® AN 305-11 Pipe and thread sealing, 200 ml, white
10023823	WEICONLOCK® AN 305-11 Pipe and thread sealing, 300 ml, white
10019939	WEICONLOCK® AN 305-11 Pipe and thread sealing, 50 ml, white

To the product detail page:

Note
The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weicon.cz

WEICON GmbH & Co. KG
(Headquarters) Germany
phone +49 (0) 251 9322 0
info@weicon.de

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com

WEICON South East Asia Pte Ltd
Singapore
Phone (+65) 6710 7671
info@weicon.com.sg

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es

WEICON Italia S.r.L.
Italy
phone +39 (0) 010 2924 871
info@weicon.it

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.
Türkiye
phone +90 (0) 212 465 33 65
info@weicon.com.tr